BRIDGE FIELDS RESOURCES SDN BHD [693996-W]

Office: No. 9-1, Jalan USJ10/1G, 47620 Subang Jaya, Selangor Darul Ehsan, Malaysia.
Factory: Lot 4, Jalan Zurah 5B, Pusat Perindustrian Zurah, 44200 Rasa, Hulu Selangor
Tel : +(603) 5633 8444 Fax : +(603) 5634 5333 Website : www.bridgefields.com
Email : sales@bridgefields.com / asmipudin@bridgefields.com

Quality Polymers for World Class Sustainability™

PRODUCT SPECIFICATION

Brand : ECOTYL - 55
Product Type : BUTYL RECLAIM GRADE
Manufacturer : BRIDGE FIELDS RESOURCES SDN. BHD. MALAYSIA

Grenyiro

Physical Properties	Results	Test Method
Tensile Strength [Mpa]	8.8 ± 5	ASTM D 412
Elongation (E.B) [%]	480 ± 100	ASTM D 412
Mooney (1-4 @ 100*C)	45 ± 5	ASTM D 1646
Hardness Shore A	50 ± 10	ASTM D 2240
Specific Gravity [%]	1.10 – 1.45	ASTM D 297

Specifications provided are general in nature

Standard Packing Specification:
Weight per Bale : 25 KGS
Bales per Pallet : 50 Bales
Crate Gross Weight : 1250 KGS
Each Bale wrapped in LDPE Bag

Full Container Load:
FCL 20'Container (with Pallet) : 20,000 KGS
FCL 20'Container (without Pallet) : 25,000 KGS

Optimum Storage Conditions:
Store in dry and closed environment far from heat source at below 30°C. No direct exposure to sunlight. In such conditions, product can be stored up to eight months.

Included with its product literature and upon the request of its customers, BFR provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although BFR believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. BFR will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of BFR products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. No license is implied or granted by BFR as to any such product, method, or process. BFR CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY BFR.